

## Dawnprene TPE 6502-NC

TPE PA6 30% gf PA6

TPE

## Features:

It is a natural color thermoplastic elastomer (TPE) material. This material combines good physical properties, chemical resistance and elasticity, designed for bonding PA6 and 30%gf PA6 applications. This grade of TPE can be processed on conventional thermoplastics equipment for injection. It is completely recyclable.

gener	al injection bond	PA6 and 30% gf PA6
RoHS		
Natural		
Pellet		
injection		
2023-03-07		
Typical Value	Unit	Test Method
1.10	g/cm <sup>3</sup>	ASTM D792
70	A	ASTM D2240
5.2	Mpa	ASTM D412
790	%	ASTM D412
2.5	Mpa	ASTM D412
3.2	Mpa	ASTM D412
32	KN/m	ASTM D624
	RoHS  Natural Pellet injection 2023-03-07  Typical Value  1.10  70  5.2  790  2.5  3.2	RoHS

0.1%

Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.1%, suggesting drying as follow process:

Drying conditions	Drying temperature/	Drying time/h
first choice	80 90	2 3
other choice	100	1

110

If drying temperature over than 110 ,it might cause materials blocking in barrel zone; if use moisture analysis meter, the temperature setting should be on 105 .



R